

Petrochina Lanzhou Petrochemical company

Product quality inspection sheet

Analysis project	Qualitative index	measured results	test method
Large an small grains,g/kg	≤ 10	9.9	SH/T 1541
Color granule,plece/kg	≤ 10	0	SH/T 1541
Snake skin granule and tail granule,piece/kg	≤ 15	6	SH/T 1541
Melt mass flow rate,g/10min	18-32	26.8	GB/T 3682.1
Tensile yield stress,Mpa	≥ 29	33.8	GB/T 1040.2
Bending modulus,Mpa	≥ 900	1362	GB/T 9341
ash,%	≤ 0.03	0.0161	GB/T 9345.1
Isotactic index,%	≥ 95	97.2	GB/ T 2412
The yellow index	≤ 4	2.4	HG/T 3862
fisheye0.8mm,piece/1520cm ²	≤ 10	6	GB/ T 6595
fisheye0.4mm,piece/1520cm ²	≤ 20	9	GB/ T 6595