

## Petrochina Lanzhou Petrochemical company

## Product quality inspection sheet

Analysis project	Qualitative index	measured results	test method
Large an small grains,g/kg	$\leq 10$	0.8	SH/T 1541-2006
Color granule,plece/kg	$\leq 5$	4	SH/T 1541-2006
Snake skin granule and tail granule,piece/kg	$\leq 15$	7	SH/T 1541-2006
Melt mass flow rate,g/10min	20-28	20	GB/T 3682.1-2008
Tensile yield stress,Mpa	$\geq 31.5$	32.2	GB/T 1040.2-2006
ash,%	$\leq 0.03$	0.03	GB/T 9345.1-2008
fisheye0.8mm,piece/1520cm <sup>2</sup>	$\leq 10$	2	GB/ T 6595-1986
fisheye0.4mm,piece/1520cm <sup>2</sup>	$\leq 20$	8	GB/ T 6595-1986
Isotactic index,%	$\geq 97$	99.7	GB/ T 2412-2008