

Petrochina Lanzhou Petrochemical company

Product quality inspection sheet

Analysis project	Qualitative index	measured results	test method
Large an small grains,g/kg	≤10	0.3	SH/T 1541-2006
Color granule,plece/kg	≤5	3	SH/T 1541-2006
Snake skin granule and tail granule,piece/kg	≤15	4	SH/T 1541-2006
Melt mass flow rate,g/10min	16-22	19	GB/T 3682.1-2008
Tensile yield stress,Mpa	≥31.5	32.3	GB/T 1040.2-2006
ash,%	≤0.03	0.03	GB/T 9345.1-2008
fisheye0.8mm,piece/1520cm <sup>2</sup>	≤10	2	GB/ T 6595-1986
fisheye0.4mm,piece/1520cm <sup>2</sup>	≤20	9	GB/ T 6595-1986
Isotactic index,%	≥97	98.1	GB/ T 2412-2008