

Petrochina Lanzhou Petrochemical company

Product quality inspection sheet

Analysis project	Qualitative index	measured results	test method
Large an small grains,g/kg	-	11	SH/T 1541
Color granule,plece/kg	≤ 5	0	SH/T 1541
Snake skin granule and tail granule,piece/kg	-	13	SH/T 1541
Melt mass flow rate,g/10min	40-50	45	GB/T 3682
Tensile yield stress,Mpa	≥ 29	30.9	GB/T 1040.2
Bending modulus,Mpa	-	1258	GB/T 9341
ash,%	≤ 0.04	0.0156	GB/T 9345.1
fisheye0.8mm,piece/1520cm ²	≤ 10	2	GB/ T 6595
fisheye0.4mm,piece/1520cm ²	≤ 40	9	GB/ T 6595
Isotactic index,%	-	97.2	GB/ T 2412
The yellow index	-	-1.4	HG/T 3862