

Petrochina Lanzhou Petrochemical company

Product quality inspection sheet

Analysis project	Qualitative index	measured results	test method
Large an small grains,g/kg	≤ 10	4	SH/T 1541-2006
Color granule,plece/kg	≤ 5	2	SH/T 1541-2006
Snake skin granule and tail granule,piece/kg	≤ 10	4	SH/T 1541-2006
Melt mass flow rate,g/10min	28~40	35.3	GB/T 3682.1-2008
Tensile yield stress,Mpa	≥ 32	35	GB/T 1040.2-2006
ash,%	≤ 0.03	0.02	GB/T 9345.1-2008
Isotactic index,%	≥ 97	97	GB/ T 2412-2008
fish-eye0.8mm,piece/1520cm ²	≤ 10	7	GB/ T 6595-86
fish-eye0.4mm,piece/1520cm ²	≤ 20	7	GB/ T 6595-86