

Petrochina Lanzhou Petrochemical company

Product quality inspection sheet

Analysis project	Qualitative index	measured results	test method
Color granule, piece/kg	≤ 20	0	SH/T 1541-2006
Melt mass flow rate, g/10min	17~23	20	GB/T 3682-2000
Density, g/cm ³	0.922-0.926	0.924	GB/T 1033.2-2010
Tensile yield stress, Mpa	≥ 7	9.2	GB/T 1040.2-2006
Tensile fracture nominal strain, %	≥ 80	504	GB/T 1040.2-2006
Notched impact strength of simply supported beams(23°C), kJ/m ²	≥ 20	61.6	GB/T 1043.1-2008